

# Oil4Sun

## Natural impregnating oil for outdoor wood

Oil4sun is an impregnating oil for finishing and protection of outdoor floors and other wooden products. Its application is simple and it is easily renewable, water resistant, does not crack and gives the wood an open pore appearance typical of an oil finish treatment.

Oil4sun is formulated with natural and synthetic oils and special additives that guarantee protection against UV rays, the cause of degradation and ageing of the wood. The light amber look of the natural version allows to homogenize and revive the tonality of any wood surface, enhancing its grain and natural warmth.

Oil4sun is available in the versions: natural, teak, wengé and grey.

### Technical data – 20 °C, 60% R.H.

Aspect	Coloured liquid
Density	0.881 – 1.086 kg/litre
Dust free	6 – 8 hours
Touch dry	12 – 24 hours
Overcoating	18 – 24 hours
Yield	15 – 20 m <sup>2</sup> /litre
Possible dilution	Diluente RMD 91
Application temperature	> 10 °C
Storage	12 months in original sealed packaging at temperature > 10 °C
Tools cleaning	Immediately after use with RMD 91 Thinner or Greencleaner
Packaging available	Jars of 1 or 2.5 litres

### Wood preparation

The surface to be treated must be free of residues from previous painting or other treatments. Proceed with sanding and finish with a grain size not greater than 100 – 120. If you want to minimize the final slipperiness of the floor in wet situations, finish with 60 – 80 grit. Clean thoroughly before applying the product. In the case of renovation of striped floors, remove the residues of the old treatments as described in the item Deep cleaning with oil removal.

### Application

After checking that the surface to be treated is dry, apply Oil4Sun with a brush or roller, taking care not to exceed the quantity. After 15 – 20 minutes remove any excess of product with a cloth, in the case of smooth floors it is possible to use a buffing machine with red pad to remove the excess of product. If after the first coat of product the appearance is thin and uneven, a second coat can be applied, after 18 – 24 hours, in the same way as the first. In the case of striped floors, we recommend a brush application.

***The rags and cloths used for the application of Oil4Sun must be abundantly wet with water immediately after use to avoid possible self-combustion.***



Varnishes  
& Finishing

## Oil4Sun



### Certificazioni

## Maintenance

For the maintenance of the surfaces treated with Oil4Sun, we recommend washing with our cleaner Deck-Soap

For extraordinary maintenance (approximately every 4 – 6 months) restore worn or poor areas using the same Oil4Sun diluted 30 – 40% with Diluente RMD91.

A correct maintenance includes both frequent cleaning of the floor and periodic restoration of the surface protection that has worn out; the frequency of these interventions obviously depends on the intensity of the traffic to which the floor is subject as well as on the environmental conditions (e.g. saltiness in seaside places).

**Deep cleaning with oil removal** – When the floor surface can no longer be restored with normal maintenance, we recommend performing a deep cleaning in order to remove the old oil. For this operation, use Re-Wood undiluted following the instructions given in the relative technical data sheet. If after washing with Re-Wood there are grey areas, these can be returned to the original color with Grey Free. After rinsing with clean water and drying, reapply Oil4Sun as described previously.

## Notes

- Some oily or resinous woods can slow down the oil drying. Make sure Oil4Sun is completely dry before putting the floor into operation.
- We recommend to protect the floor from rain for at least 24 hours after applying the oil to allow a correct drying.
- Although it is ready for light traffic after a few hours, maximum care is recommended in the first week.
- Always close the container tightly after use.
- We recommend to always carry out a preliminary application to evaluate the effect.
- To achieve the desired final effect, always carry out treatment tests before operating on the entire surface.
- Pay attention to the batch numbers of the coloured products. Always use a single batch for each applied coat. If it is not possible, mix the different lots together before application. Apply the product at a temperature above 10 °C.

## Safety regulations

Professional use product. Strictly comply with what is stated on the labelling and consult the safety data sheet before using the product.

Rags, cloths and sponges soaked in the product can ignite due to self-combustion: wet them abundantly with water, allow them to dry and dispose of them in accordance with current legislation.

## Disposal

Dispose of the unused product and empty packaging in accordance with the provisions of the local legislation in force.



Varnishes  
& Finishing

## Oil4Sun



## Certificazioni

The recommendations in this technical data sheet are given for information only and do not bind our responsibility in any way since the methods and conditions of use of the product are beyond our control. We recommend checking the actual suitability for the intended use.

Rev 11 – 03/04/2023. This technical data sheet replaces the previous one.